

Chemical Resistance Guide

MAXIMUM RECOMMENDED OPERATING TEMPERATURES

GASKET MATERIALS	BUNA N	250°F
	ETHYLENE PROPYLENE	350°F
	FLUOROELASTOMER	450°F
	PTFE	500°F
FILTER MEDIA	POLYESTER	300°F
	POLYPROPYLENE	180°F
	NYLON	325°F
HOUSING MATERIALS	CARBON STEEL	400°F
	304 STAINLESS STEEL	400°F
	316 STAINLESS STEEL	400°F
	PVC	150°F
	POLYPROPYLENE	150°F

NOTES: Maximum temperature at standard vessel design pressure.
For higher temperatures consult Rosedale Products, Inc.

Key

- = Recommended for most conditions up to the maximum temperature of the material.
 - = Fair. May be acceptable, but testing is recommended.
 - = Not recommended.
 - = No data available. Customer testing required.
- Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Acetaldehyde	●	●	●	●	●	●	●	●	●	●	●	120
Acetamide	●	●	●	●	●	●	●	○	○	○	○	○
Acetic Acid 5%	●	●	●	●	200	●	200	●	●	70	●	●
Acetic Acid 50%	●	●	●	●	200	●	70	●	●	70	●	●
Acetic Acid 80%	●	●	●	●	200	●	70	●	●	70	●	●
Acetic Acid 100%	●	●	●	●	200	150	70	●	●	70	●	●
Acetic Anhydride	●	●	●	●	○	●	○	●	●	●	●	●
Acetone	●	●	●	●	★	80	●	●	●	●	●	70
Acetophenone	●	●	●	●	●	●	●	200	●	●	○	●
Acetyl Chloride	●	●	●	●	●	●	●	●	●	●	○	●
Acetylene	●	●	●	●	○	●	●	●	●	70	○	○
Acrylic Acid	○	○	●	●	70	150	●	●	○	●	○	●
Acrylonitrile	●	●	70	●	70	70	70	●	●	●	○	70
Adipic Acid	○	○	○	○	○	●	●	●	●	70	○	○
Air-Compressed	●	●	●	●	●	●	●	●	●	70	●	●
Aluminum Acetate	●	●	●	●	○	70	○	●	●	70	○	○
Aluminum Ammonium Sulfate	○	○	○	○	○	●	○	○	○	○	○	●
Aluminum Chloride 5%	●	●	●	●	70	200	70	●	●	70	●	●
Aluminum Fluoride 5%	●	●	●	●	○	70	○	●	●	70	70	70
Aluminum Hydroxide	●	○	●	●	●	70	●	●	●	70	70	70
Aluminum Nitrate	●	●	●	●	○	70	○	●	●	70	70	70
Aluminum Sulfate	●	●	●	●	70	180	70	●	●	70	●	●
Amino Acids	○	○	●	●	○	○	○	○	○	○	○	○
Ammonia Gas (Dry)	70	●	●	○	150	20	○	●	●	70	●	●
Ammonium Bicarbonate	●	●	●	●	○	70	○	●	●	○	○	○
Ammonium Bromide 10%	●	●	●	●	○	○	○	○	○	○	○	○
Ammonium Carbonate 10%	●	●	●	●	●	180	●	●	●	70	●	●
Ammonium Chloride 10%	●	●	●	●	70	180	●	●	●	70	●	●
Ammonium Fluoride 10%	●	●	○	●	○	70	○	○	●	70	70	70
Ammonium Hydroxide 30%	●	●	●	●	70	200	100	●	●	70	●	●
Ammonium Nitrate 5%	●	●	●	●	70	●	●	●	●	70	●	●
Ammonium Phosphate	●	●	●	●	○	140	○	●	●	70	●	●
Ammonium Sulfate 5%	●	●	●	●	70	170	○	●	●	70	70	70
Ammonium Thiocyanate	●	●	○	●	70	○	70	●	●	70	○	○
Amyl Acetate	●	●	●	●	●	70	70	○	○	○	○	●
Amyl Alcohol	●	●	●	●	70	70	70	●	●	70	●	●
Aniline	●	●	160	●	70	180	70	●	●	70	●	●
Aqua Regia	●	●	●	●	●	75	●	●	●	70	●	●
Arsenic Acid	●	●	●	●	○	●	●	●	●	70	●	●

Key

- = Recommended for most conditions up to the maximum temperature of the material.
 - = Fair. May be acceptable, but testing is recommended.
 - = Not recommended.
 - = No data available. Customer testing required.
- Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Asphalt	●	●	●	●	○ 70	○		●	●	●	○	○
Aviation Fuel	●	●	●	●	70	80	●	●	●	●	○	●
Banana Oil	●	●	●	●	70	●	70	●	●	●	●	70
Barium Carbonate	●	●	●	●	●	70	●	●	●	●	70	○
Beer	●	●	●	●	○	●	○	●	●	●	70	○
Beet Sugar Liquors	●	●	●	○	●	○	●	●	●	●	70	○
Benzene	●	●	70	●	●	●	●	●	●	●	●	●
Bromine (Dry)	●	●	●	●	●	70	●	●	●	●	●	○
Bromine (Wet)	●	●	●	●	●	●	●	●	●	●	80	○
Butane	●	●	●	●	250	70	●	●	●	●	70	○
Butanoic Acid	○	○	○	○	○	○	●	○	●	●	○	○
Butyl Acetate	●	●	●	●	●	200	●	●	●	●	70	○
Butyl Alcohol	●	●	●	●	100	●	●	●	●	●	70	●
Butyl Cellosolve	●	●	●	○	○	70	○	○	●	●	○	○
Butyl Chloride	○	○	○	○	○	○	○	●	●	●	○	○
Butylene	●	●	●	●	○	○	70	●	○	●	○	○
Butyric Acid	●	●	●	●	●	●	●	●	●	●	●	●
Calcium Chloride	●	●	●	200	●	●	●	●	●	●	70	●
Calcium Hydroxide 5%	●	●	●	●	100	200	●	●	●	●	70	●
Calcium Hypochlorite	●	●	●	●	●	200	●	●	●	●	70	●
Cane Sugar Liquors	●	●	●	●	●	●	●	●	●	●	70	●
Carbolic Acid (Phenol)	●	●	●	●	●	70	●	●	●	●	70	●
Carbon Dioxide (Dry)	●	●	●	●	○	●	100	●	●	●	●	●
Carbon Disulfide	●	●	●	●	70	●	70	●	●	●	●	●
Carbon Tetrachloride	●	●	●	●	●	100	●	●	●	●	80	70
Carbonated Water	●	●	●	●	○	●	100	●	●	●	70	●
Carbonic Acid	●	●	●	●	○	●	100	●	●	●	70	70
Castor Oil	●	●	●	●	○	●	○	●	●	●	70	●
Caustic Potash	●	●	●	●	○	●	●	★	●	●	70	●
Caustic Soda	●	●	●	●	○	●	●	100	●	●	70	●
Cellosolve	●	●	●	○	○	70	○	100	○	100	70	○
Chloracetic Acid	●	●	●	●	●	70	●	●	●	●	70	●
Chlorine Gas (Dry)	●	●	●	●	○	●	●	70	●	●	80	●
Chlorine Gas (Wet)	●	●	●	●	○	●	●	●	●	●	80	●
Chlorobenzene	●	●	●	●	200	●	200	●	●	●	●	70
Chloroform (Dry)	●	●	●	●	70	70	●	●	●	●	●	●
Chromic Acid	●	●	●	●	●	80	●	●	●	●	80	80
Cider	●	●	●	●	○	●	○	●	●	●	70	●

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Citric Acid	●	●	●	●	●	●	●	●	●	70	●	●
Cod Liver Oil	●	●	●	●	○	●	○	●	●	70	●	●
Coffee Extract	●	○	●	●	○	●	○	●	●	●	●	●
Cola Syrup	○	○	○	●	70	70	70	○	●	●	○	70
Copper Sulfate	●	●	●	●	70	●	●	●	●	70	●	●
Corn Oil	●	●	●	●	○	100	●	●	●	70	70	70
Cottonseed Oil	●	●	●	●	●	100	●	●	●	70	70	70
Creosol	○	●	●	●	●	●	●	○	○	○	○	○
Creosote	●	●	●	●	○	●	○	●	●	70	●	●
Cresylic Acid	●	●	●	●	●	●	●	○	○	70	●	●
Cyclohexane	●	●	●	●	200	●	○	●	●	70	●	●
Cyclohexanol	○	○	○	○	○	150	○	○	○	○	○	○
Cyclohexamine	●	●	●	●	200	●	●	70	○	70	●	●
DDT Solution	○	○	●	●	○	●	○	○	●	●	○	●
Dextrose	●	●	●	●	○	●	○	●	●	70	70	70
Diacetone Alcohol	●	●	●	●	○	70	○	●	●	70	●	●
Dibutyl Phthalate	●	●	●	●	○	70	○	●	●	70	○	●
Dichloroethane	●	●	●	●	○	●	○	○	●	70	○	○
Dichloroethylene	○	○	○	○	○	70	70	○	○	○	○	○
Diesel Fuel	●	●	●	●	○	120	●	●	●	80	120	120
Diethanolamine	●	●	●	●	●	●	●	○	○	○	○	●
Diethylene Glycol	●	●	●	●	●	●	●	●	●	○	○	●
Dimethyl Formamide	●	○	○	200	200	200	200	○	70	70	○	●
Diphenyl Oxide	●	●	●	●	○	70	○	●	●	70	○	70
Dowtherm	●	●	●	●	○	70	○	●	●	70	○	70
Epichlorohydrin	●	●	●	●	●	120	●	○	○	○	○	120
Ethanol	●	●	●	●	●	●	●	●	●	○	○	●
Ethanolamine	●	●	●	●	○	70	○	●	●	70	○	70
Ether	●	●	●	●	95	●	●	●	●	●	●	●
Ethyl Acetate	●	●	●	●	●	120	●	●	●	70	120	120
Ethyl Cellulose	●	●	●	●	○	70	○	●	●	○	○	70
Ethyl Chloride (Dry)	●	●	●	●	○	●	○	200	●	70	○	○
Ethylene Diamine	●	●	●	●	○	70	70	70	●	70	○	70
Ethylene Glycol	●	●	●	●	●	●	70	●	●	70	○	70
Ethylene Oxide	●	●	●	●	○	●	○	●	●	70	○	○
Fatty Acids	●	●	●	●	●	●	●	●	●	70	○	●
Ferric Chloride 1%	●	●	●	●	200	●	●	●	●	70	○	●

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Ferric Chloride	●	●	●	●	200	○	●	●	●	●	70	70
Ferric Nitrate	●	●	●	●	70	○	○	○	○	●	70	○
Ferric Sulfate 5%	●	●	●	●	70	●	70	●	●	●	70	●
Ferrous Chloride	●	○	○	●	70	●	70	●	○	70	○	●
Fish Oils	●	○	○	●	○	70	○	●	●	●	70	●
Fluosilicic Acid	●	●	●	●	○	70	○	●	○	●	70	●
Formaldehyde 10%	80	●	●	●	●	●	●	●	●	●	70	●
Formalin 40%	●	●	●	●	○	●	○	●	●	●	70	70
Formic Acid (Dilute)	●	●	●	●	●	●	●	●	●	●	70	●
Formic Acid (Conc.)	●	●	●	○	70	●	●	●	●	●	○	○
Freon 12	●	●	●	●	○	●	100	●	●	●	●	●
Freon 22	●	●	●	●	○	●	100	●	●	●	●	●
Fruit Juices	●	○	●	●	○	70	○	●	●	●	70	70
Fuel Oils	●	●	●	●	●	70	●	●	●	●	70	70
Furfural	●	●	●	●	○	70	○	●	●	●	●	●
Gas-Natural	●	●	●	●	●	70	●	●	●	●	70	70
Gasoline-Sour	●	●	●	●	○	●	70	●	●	●	80	●
Gasoline-Motor	●	●	●	●	○	●	70	●	●	●	80	●
Gasoline-Aviation	●	●	●	●	○	●	70	●	●	●	80	●
Gelatin	●	●	●	●	●	●	●	●	●	●	70	70
Glucose	●	●	●	●	○	●	○	●	●	●	70	70
Glycerine-Glycerol	●	●	●	●	●	●	●	●	●	●	70	70
Glycol	●	●	●	●	●	●	●	●	●	●	70	●
Glycol Monoether	●	●	●	●	○	70	○	○	●	●	70	70
Grease	●	●	●	●	○	●	○	●	●	●	70	●
Green Sulfate Liquor	●	●	●	●	○	70	●	●	●	●	○	○
Gum Arabic	○	●	○	●	○	○	○	○	●	○	○	○
Helium	●	●	●	●	●	●	●	●	●	●	○	70
Hexane	●	●	●	●	●	70	●	●	●	●	80	70
Honey	●	●	●	●	○	○	○	○	●	●	○	○
Hydraulic Oil-Petroleum Base	●	●	●	●	●	70	●	●	●	●	70	70
Hydraulic Oil-Phosphate Ester	●	●	●	●	●	70	●	●	●	●	○	70
Hydrazine	●	●	●	●	○	○	○	○	○	●	○	○
Hydrobromic Acid 10%	●	●	●	●	70	150	●	●	●	●	70	●
Hydrobromic Acid 50%	●	●	●	●	○	150	●	●	●	●	70	●
Hydrochloric Acid 5%	160	●	●	●	●	●	●	●	●	●	●	●

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Hydrochloric Acid 30%	70	70	70	●	●	●	●	●	●	●	●	70
Hydrocyanic Acid 5%	●	●	●	●	○	70	○	●	●	●	70	70
Hydrocyanic Acid	●	●	●	●	○	70	○	●	●	●	70	70
Hydrofluoric Acid 10%	80	70	○	●	●	●	●	●	●	●	80	●
Hydrofluoric Acid 50%	○	○	●	●	○	70	●	●	●	●	○	70
Hydrogen Gas	●	●	●	●	○	●	○	●	●	●	70	●
Hydrogen Peroxide 5%	●	●	●	●	●	150	●	●	●	●	70	140
Hydrogen Peroxide 30%	●	●	●	●	●	70	●	●	●	●	70	70
Hydrogen Sulfide (Dry)	70	●	●	●	○	70	○	●	●	●	80	70
Hydrogen Sulfide (Wet)	●	●	●	●	○	●	○	●	●	●	70	●
Hydroquinone	●	●	●	●	70	70	○	○	●	●	70	70
Insulating Oil	●	●	●	●	○	○	○	●	●	●	○	○
Iodine	●	●	●	●	●	●	●	●	●	●	●	70
Isopropyl Acete	●	●	●	●	○	○	○	○	○	●	○	○
Isopropyl Alcohol	●	●	●	●	70	●	○	●	●	●	70	●
Kerosene	●	●	●	●	●	70	●	●	●	●	70	70
Ketchup	●	○	●	●	○	70	○	○	●	●	○	70
Lactic Acid	70	70	●	●	70	●	70	○	●	●	70	●
Lard Oil	●	●	●	●	●	80	●	●	●	●	70	80
Latex (Natural)	●	○	●	●	○	70	○	●	●	●	○	70
Lead Acetate	●	●	●	●	●	●	●	●	●	●	70	70
Lime-Sulfur	●	●	●	●	○	70	○	○	●	●	○	70
Linoleic Acid	●	●	●	●	○	●	●	●	●	●	70	●
Linseed Oil	●	●	●	●	●	●	●	●	●	●	70	100
Lithium Bromide	○	○	○	●	○	70	○	●	○	●	○	70
Lithium Carbonate	●	○	○	●	○	70	○	○	○	○	○	70
Lithium Chloride	●	●	○	○	●	●	●	●	●	●	○	70
Lithium Hydroxide	●	●	○	○	○	●	●	●	●	●	○	70
Lube Oil	●	●	●	●	○	70	●	●	●	●	70	70
Lye	●	●	●	●	●	●	●	130	●	●	70	●
Magnesium Chloride	●	●	●	●	70	180	70	●	●	●	70	●
Magnesium Hydroxide	●	●	●	●	○	●	○	●	●	●	70	●
Magnesium Sulfate	●	●	●	●	○	180	○	●	●	●	70	70
Mayonnaise	●	○	●	●	○	70	○	●	●	●	○	70
Melamine Resins	●	○	●	●	○	70	○	○	●	●	○	70
Mercuric Chloride 10%	●	●	●	●	70	70	○	●	●	●	70	70
Mercurous Nitrate	●	●	○	●	○	70	○	●	●	●	70	70

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Mercury	●	●	●	●	70	70	70	●	●	●	70	70
Methane	●	●	●	●	○	70	○	●	●	●	70	70
Methylene Chloride	●	●	●	●	100	●	100	100	150	212	●	●
Methyl Alcohol	●	●	●	●	●	●	●	●	●	●	70	●
Methyl Acetate	●	●	●	●	●	70	●	●	●	●	○	70
Methyl Cellosolve	●	●	●	●	○	70	○	●	●	●	●	70
Methyl Ethyl Ketone	●	●	●	●	70	●	●	●	●	●	●	70
Milk	●	●	●	●	●	●	●	●	●	●	●	●
Mineral Oil	●	●	●	●	○	70	○	●	●	●	70	70
Molasses	●	●	●	●	200	70	200	●	●	●	70	70
Monoethanolamine	●	●	●	●	○	70	○	●	●	●	○	70
Mustard	●	○	●	●	○	70	○	●	●	●	○	70
Naptha	●	●	●	●	200	70	200	●	●	●	70	70
Napthalene	●	●	●	●	70	70	70	●	●	●	●	●
Nickel Chloride	●	●	●	●	70	200	●	●	●	●	70	100
Nickel Sulfate	●	●	●	●	○	●	●	●	●	●	70	●
Nitric Acid 10%	●	●	70	●	●	210	●	●	●	●	70	100
Nitric Acid 20%	●	●	70	●	●	180	●	●	●	212	70	70
Nitric Acid 50%	●	●	70	●	●	70	●	●	212	212	70	70
Nitric Acid Fuming	●	●	●	●	●	●	●	●	125	125	●	●
Nitrobenzene 10%	●	●	●	●	200	●	200	●	●	●	●	●
Nitrobenzene	●	●	●	●	200	●	200	●	●	●	●	●
Nitrogen	●	●	●	●	●	●	●	●	●	●	○	●
Nitrous Oxide	●	○	○	●	○	○	○	●	●	●	70	70
Oil, Crude	●	●	●	●	●	70	●	●	●	●	70	70
Oleic Acid 5%	●	●	●	●	○	180	●	●	●	●	70	70
Oleic Acid	●	●	●	●	150	120	●	●	●	●	●	●
Oleum	●	●	●	●	○	●	●	●	●	●	●	●
Olive Oil	●	●	●	●	○	70	○	●	●	●	70	70
Oxalic Acid 5%	●	●	●	●	●	180	70	○	●	●	70	●
Palm Oil	●	○	●	●	○	70	○	●	●	●	○	70
Pentane	●	●	●	●	○	70	●	●	●	●	80	70
Perchloroethylene (Dry)	●	●	●	●	200	●	200	●	●	●	70	●
Petroleum Ether	●	●	●	●	●	70	●	●	●	●	70	70
Petroleum Oil-Refined	●	●	●	●	●	70	●	●	●	●	70	70
Petroleum Oil-Sour	●	●	●	●	●	70	●	●	●	●	70	70
Phenol	●	●	●	●	●	190	●	●	●	●	70	●

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Phenol-Formaldehyde Resin	○	●	○	●	○	○	○	●	●	●	○	○
Phosphoric Acid 1%	●	●	●	●	210	210	●	●	212	●	70	●
Phosphoric Acid 10%	●	●	●	●	210	210	70	●	212	●	70	●
Phosphoric Acid 50%	70	●	●	●	●	180	●	●	212	●	70	●
Phosphoric Acid 80%	70	●	●	●	●	180	●	●	●	●	70	●
Picric Acid (H ₂ O Sol'n.)	●	●	●	●	○	120	○	●	●	●	●	120
Pine Oil	●	●	●	●	70	70	70	●	●	●	○	70
Plating Solutions												
-Arsenic	●	●	●	●	○	150	○	●	○	●	○	150
-Brass Cyanide	●	●	○	●	○	●	○	●	●	○	70	●
-Bronze Cyanide	●	●	●	●	○	70	○	●	○	○	70	70
-Cadmium Cyanide	●	●	●	●	○	●	○	●	●	●	70	●
-Cadmium Fluoborate	●	●	●	●	○	70	○	○	●	●	70	70
-Copper Cyanide	●	●	●	●	○	●	○	●	●	●	70	●
-Gold Cyanide	●	●	●	●	○	●	○	○	●	●	●	●
-Iron Chloride	●	●	●	●	○	●	●	○	●	●	●	●
-Iron Sulfate	●	●	●	●	○	140	140	●	○	●	●	140
-Lead Alkali	●	●	●	●	○	●	●	●	○	●	70	○
-Lead Fluoborate	●	●	●	●	○	○	100	○	●	●	70	○
-Nickel Bright Chloride	●	●	●	●	○	70	○	○	●	●	70	70
-Nickel Dull Chloride	○	●	●	●	○	○	○	○	●	●	70	○
-Nickel Dull Fluoborate	●	●	●	●	○	●	170	○	○	●	●	●
-Silver	●	●	●	●	○	80	○	●	●	●	70	80
-Tin Acid	●	●	●	●	○	70	70	○	○	○	80	70
-Tin Fluoborate	●	●	●	●	○	100	100	○	●	●	80	100
-Zinc Cyanide	●	●	●	●	○	100	○	●	●	●	70	100
-Zinc Fluoborate	○	●	●	●	○	○	130	○	○	●	70	○
Potassium Acetate 10%	●	●	●	●	○	70	○	●	●	●	○	70
Potassium Bisulfate 10%	○	○	○	●	●	70	●	○	●	●	○	70
Potassium Carbonate 10%	●	●	●	●	●	180	●	●	●	●	●	●
Potassium Chloride 5%	●	●	●	●	70	180	○	●	●	●	70	●
Potassium Chromate 10%	●	●	●	●	○	70	○	○	●	●	70	70
Potassium Cyanide 5%	●	●	●	●	○	●	●	●	●	●	70	●
Potassium Ferrocyanide 10%	●	●	●	●	○	70	○	●	●	●	70	70
Potassium Permanganate 5%	●	●	●	●	●	150	●	●	●	●	70	70
Potassium Sulfate 5%	●	●	●	●	120	180	120	●	●	●	70	●
Propane	●	●	●	●	250	100	200	●	●	●	80	100
Propionic Acid	○	●	○	●	●	70	●	●	●	●	○	70
Propylene Glycol	●	●	●	●	●	70	●	●	●	●	○	70

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Propylene Oxide	●	●	●	●	○	70	○	○	○	○	○	70
Pyridine	●	●	●	○	●	●	●	●	●	○	○	●
Sea Water	●	●	●	●	210	●	240	●	●	●	●	●
Shellac	●	●	○	●	○	70	○	●	●	○	○	70
Silver Nitrate	●	●	●	●	●	●	●	●	●	○	70	●
Soda Ash	●	●	●	●	70	70	●	●	●	●	70	70
Sodium Acetate	●	●	●	●	●	●	●	●	●	●	70	●
Sodium Bicarbonate	●	●	●	●	○	●	○	●	●	●	70	●
Sodium Bisulfate	●	●	●	●	70	150	●	●	●	●	70	70
Sodium Bisulfite	●	●	●	●	●	180	●	●	○	100	○	70
Sodium Borate	●	●	●	●	○	70	○	●	●	●	70	70
Sodium Carbonate	●	●	●	●	●	●	●	●	●	●	70	70
Sodium Chlorate	●	○	●	●	○	180	○	○	●	●	70	120
Sodium Chloride 10%	●	●	●	●	●	●	●	●	●	●	70	●
Sodium Cyanide	●	●	●	●	●	●	●	●	●	●	70	●
Sodium Fluoride 5%	●	●	●	●	○	70	○	●	●	●	70	●
Sodium Hydroxide 5%	●	●	●	●	70	●	●	●	●	●	70	70
Sodium Hydroxide 20%	●	●	●	●	●	●	●	●	●	●	70	●
Sodium Hydroxide 40%	●	●	●	●	●	●	●	●	●	●	70	70
Sodium Hypochlorite 5%	●	●	●	●	●	120	●	●	●	●	70	70
Sodium Metaphosphate	●	●	●	●	○	70	○	●	●	●	70	70
Sodium Nitrate 5%	●	●	○	●	70	180	70	●	●	●	70	70
Sodium Perborate 1%	●	●	●	●	160	180	○	●	●	●	70	●
Sodium Peroxide	●	●	●	●	●	70	○	●	●	●	70	70
Sodium Phosphate	●	●	●	●	70	180	●	●	●	●	120	●
Sodium Polysulfide	○	○	○	●	○	○	○	○	●	●	○	○
Sodium Silicate	●	●	●	●	○	180	○	●	●	●	70	●
Sodium Sulfate	●	●	●	●	70	180	70	●	●	●	70	●
Sodium Sulfide	●	●	●	●	●	180	●	●	●	●	●	●
Sodium Thiosulfate	○	○	○	●	70	70	70	●	●	●	70	70
Soybean Oil	●	●	●	●	70	180	○	●	●	●	70	●
Stannic Chloride 5%	●	●	●	●	○	100	●	●	●	●	70	100
Stannous Chloride 5%	●	●	●	●	70	70	70	●	●	●	70	70
Starch	●	●	●	●	○	●	○	●	●	●	70	70
Steam	○	●	○	●	○	220	240	●	●	●	●	●
Steacates	●	●	●	●	○	●	●	●	●	●	70	●
Stearic Acid	●	●	○	●	○	●	●	●	●	●	70	●
Stoddard Solvent	●	●	●	●	70	70	70	●	●	●	●	70

Key

- = Recommended for most conditions up to the maximum temperature of the material.
- = Fair. May be acceptable, but testing is recommended.
- = Not recommended.
- = No data available. Customer testing required.

Number (i.e. 70) = Maximum temperature in degrees F°

	GASKET MATERIALS				FILTER MEDIA			HOUSING MATERIALS				
	Buna N	Ethylene Propylene	Fluoroelastomer	PTFE	Polyester	Polypropylene	Nylon	Carbon Steel	304 Stainless Steel	316 Stainless Steel	PVC	Polypropylene
Sucrose Solutions	●	●	●	●	○	●	○	●	●	●	70	70
Sulfate Liquors	●	●	●	●	○	70	●	○	●	●	70	●
Sulfur Dioxide (Dry)	●	●	●	●	○	●	●	●	●	●	70	●
Sulfur Trioxide (Dry)	●	●	●	●	○	●	●	●	●	●	70	●
Sulfuric Acid 5%	●	●	●	●	150	●	●	●	●	●	70	●
Sulfuric Acid 50%	●	●	●	●	70	180	●	●	●	●	70	70
Sulfuric Acid 96%	●	●	●	●	●	70	●	●	●	●	70	●
Sulfuric Acid Fuming	●	●	●	●	●	●	●	●	●	●	70	●
Sulfurous Acid	●	●	●	●	○	●	●	●	●	●	70	●
Tannic Acid 10%	●	●	●	●	70	●	70	●	●	●	70	●
Tartaric Acid	●	●	●	●	○	150	○	●	●	●	70	70
Tetrachlorethylene (Dry)	●	●	●	●	○	●	212	●	●	●	70	70
Tetrachloroethane	●	●	●	○	70	70	70	75	●	●	70	70
Tetrahydrofuran	●	●	●	●	○	70	100	●	●	●	70	70
Toluene	●	●	●	●	70	120	●	●	●	●	70	120
Transformer Oil	●	●	●	●	○	120	○	●	●	●	70	120
Trichloroethylene (Dry)	●	●	●	●	70	●	70	●	●	●	70	70
Triethanolamine	●	●	●	●	70	70	○	●	●	●	70	70
Trisodium Phosphate	●	●	○	●	70	120	70	○	●	●	70	120
Tung Oil	●	●	●	●	○	70	○	●	●	●	70	70
Turpentine	●	●	●	●	70	70	●	●	●	●	80	70
Urea-Formaldehyde Resin	○	○	○	●	○	○	○	●	○	○	○	○
Vanilla Extract	○	○	○	●	○	●	○	○	●	●	○	70
Varnish	●	●	●	●	○	●	●	●	●	●	○	●
Vegetables Oils	●	●	●	●	○	100	●	●	●	●	○	100
Vinegar	●	●	●	●	○	150	●	●	●	●	70	70
Water-Fresh	●	●	●	●	210	●	240	●	●	●	70	70
Water-Salt	●	●	●	●	210	●	240	●	●	●	70	70
Waxes	○	○	●	●	○	70	○	●	●	●	○	●
Whiskey	●	●	●	●	○	70	●	●	●	●	70	70
Wine	●	●	●	●	○	70	●	●	●	●	70	70
Xylene	●	●	●	●	●	●	●	●	●	●	●	●
Zinc Bromide	●	○	○	●	○	●	●	○	○	●	○	●
Zinc Cyanide	●	○	○	○	○	●	●	●	●	●	○	●
Zinc Sulfate	●	●	●	●	●	●	●	●	●	●	70	70

Conversion Information

Conversion Information U.S. Mesh to Micron Particle Size

COMPARATIVE PARTICLE SIZE

U. S. MESH	INCHES	MICRONS	U.S. MESH	INCHES	MICRONS
3	.265	6730	40	.0165	420
3-1/2	.223	5660	45	.0138	354
4	.187	4760	50	.0117	297
5	.157	4000	60	.0098	250
6	.132	3360	70	.0083	210
7	.111	2830	80	.0070	177
8	.0937	2380	100	.0059	149
10	.0787	2000	120	.0049	125
12	.0661	1680	140	.0041	105
14	.0555	1410	170	.0035	88
16	.0469	1190	200	.0029	74
18	.0394	1000	230	.0024	63
20	.0331	841	270	.0021	53
25	.0280	707	325	.0017	44
30	.0232	595	400	.0015	37
35	.0197	500			

SCREEN MICRON AND MESH RATINGS

MICRON or MESH RATING	ROSEDALE MESH USED	MIN. BUBBLE POINT IN INCHES (H ₂ O)
2 MICRON	325X2300DT*	12.0
5 MICRON	200X1400DT	9.5
10 MICRON	165X1400DT	6.0
20 MICRON	165X800DT	4.8
40 MICRON	80X700DT	3.5
200 MESH	200P**	-
150 MESH	150P	-
100 MESH	100P	-
80 MESH	80P	-
60 MESH	60P	-
40 MESH	40P	-

* DT = Dutch Twilled Weave **P = Plain Weave

VISCOSITY CONVERSION CHART

Viscosity Measurement Method	CPS								TEMPERATURE = 77°F			
	10	20	50	100	200	500	1000	2000	5000	10,000	20,000	50,000
ASTM, 07				72	143	357	715	1430	3750	7150	14,300	35,700
ASTM, 10					42	104	208	417	1041	2080	4170	10,410
ASTM, 15						24	48	95	238	476	953	2,380
ASTM, 20						8	16	33	82	164	328	820
ASTM, 25							7	14	36	72	143	357
Brookfield	10	20	50	100	200	500	1000	2000	5000	10,000	20,000	50,000
Demmier #1				32	63	156	312					
Demmier #10				3	6	15	31					
Engler (degrees)				14	27	68	137	274	685	1370	2,740	6,850
Engler (sec.)				690	1300	3460	7000	4,000		70,500		
Ford #3				42	84	208	416	834	2081	4160	8,340	20,810
Ford #4				30	55	135	270	540	1350	2700	5,400	13,500
Fisher #1	200	30										
Fisher #2		15	24	50								
Gardner-Holdt (units)	A-3	A-2	A	D	H	S	W	Y-Z	Z3	Z5	Z6-Z7	Z7-Z8
Gardner-Holdt (sec.)						5	10	20	50	100	200	500
Gardner-Verticle (sec.)						5	10	20	50	100	200	500
Krebs-Stormer (units)	85	105	140			67	85	105	140			
Parlin 7				77	154	385	770	1540	3850	7700	15,400	38,500
Parlin 10				21	42	104	208	416	1040	2080	4,160	10,400
Parlin 15					10	25	47	93	232	465	930	2,320
Parlin 20						8	17	33	83	167	333	833
Parlin 25								15	36	72	143	357
Parlin 30									19	38	77	192
Saybolt Furol			24	48	96	238	476	954	2380	4760	9,540	23,800
Saybolt Universal (SUS)		96	238	476	954	2380	4760	9540	23,800	47,600	95,400	
Zahn G1		38	60	100	267	667	1332	2670	6670	13,320	26,700	66,700
Zahn G2		16	24	42	82	161	323	645	1610	3,230	6,450	16,100
Zahn G3					27	58	113	204	510	1,020	2,040	5,100
Zahn G4					19	38	71	160	400	800	1,600	4,000
Zahn G5					13	27	50	97	212	424	848	2,120

COMPARATIVE FINENESS DATA

HEGMAN(S) SCALE	PRODUCTION CLUB SCALE	DEPTH OF MILS	WELLS MICRON	CLOSEST U.S. MESH SIZE
0	0.00	4.0	100.00	140
1	1.25	3.50	87.50	170
2	2.50	3.00	75.00	200
3	3.75	2.50	62.50	230
4	5.00	2.00	50.00	325
5	6.25	1.50	37.50	-
6	7.50	1.00	25.00	400
7	8.75	0.50	12.50	-
7-1/2		0.25	6.25	-
8	10.00	0.00	0.00	-

APPROXIMATE VISCOSITY OF COMMON LIQUIDS

LIQUID	VISCOSITY CPS	@ TEMPERATURE °F	LIQUID	VISCOSITY CPS	@ TEMPERATURE °F
Asphalt, Virgin	7,250	250	Neasfoot Oil	230	100
Asphalt Emulsion	2,100	300		130	130
Type I	4,000	100	Oils-		
	1,025	100	Fuel Oil No. 1	37	70
Asphalt Emulsion,			Fuel Oil No. 2	33	100
Types II, V & VI	575	77	Fuel Oil No. 5	500	100
	220	100		175	130
Black Liquor	3,100	122	Fuel Oil No. 6	1,725	122
	1,525	130		480	160
Bone Oil	220	130	SAENo. 10	200	100
	65	212		105	130
Carbolic Acid	65	65	SAE No. 20	320	100
Castor Oil	1,350	100		150	130
	525	130	SAE No. 30	490	100
Caustic Soda Solution				220	130
20% NaOH	40	65	SAE No. 50	1,275	100
30%NaOH	58	65		95	210
40%NaOH	110	65	SAE No. 70	2,700	100
Cocoanut Oil	144	100		140	210
	78	130	SAE No. 90 Trans-		
Cod Oil	150	100	mission Lube	1,150	100
	95	130		400	130
Cottonseed Oil	176	100	SAE No. 140 Trans-		
	100	130	mission lube	1,625	130
Glucose	67,500	100		160	210
	7,500	150	Olive Oil	200	100
Glycerine (100%)	2,950	68.6		115	130
	813	100	Peanut Oil	250	100
Glycol:				145	130
Propylene	240	70	Petrolatum	100	130
Triethylene	190	70		77	160
Diethylene	150	70	Printers' Ink	6,250	100
Ethylene	90	70		2,100	130
Insulating Oil	115	70	Rosin (Wood)	25,500	190
	65	100		10,300	200
Kerosene	35	68	Sulfuric Acid (100%)	75.7	68
	32.6	100	Turbine Lube Oil	420	100
Lard	287	100	Turpentine	33	60
	160	130		32.6	100
Linseed Oil, Raw	143	100	Varnish-Spar	1,425	68
	93	130		650	100
Molasses, C	135,000	100			
(Blackstrap of final)	40,000	130			